


# INDO GARNET

**GRADE : # 12/20**

## SIEVE ANALYSIS

Mesh	Micron	Retained %	
		Spec	Typical
16	1180	0 - 20	5.34
20	850	> 40	60.19
30	600	30 - 50	33.96
40	425	0 - 10	0.49
50	300	0 - 2	0.02



## MINERAL COMPOSITION

Minerals	Specification (%)	Typical (%)
Garnet	Min 99.00	99.86
Ilmenite	Max 00.50	00.05
Others	Max 00.50	00.09

## PHYSICAL CHARACTERISTICS

Minerals	Specification	Typical
Specific Gravity	4.0 - 4.3	4.12
Conductivity	Max 150 $\mu$ s/cm	58.12 $\mu$ s/cm
Chloride	Max 25ppm	6.32 ppm
Hardness	Min 7 Moh's Scale	> 7 Moh's Scale
Bulk Density	2.0 - 2.7 g/cm <sup>3</sup>	2.42 g/cm <sup>3</sup>
Suspended Solids	Max 1500 mg/l	1050 mg/l

## CHEMICAL COMPOSITION

Elements	Specification (%)	Typical (%)
SiO <sub>2</sub>	32 - 40	36.44
Al <sub>2</sub> O <sub>3</sub>	18 - 24	20.26
Fe <sub>2</sub> O <sub>3</sub>	28 - 35	33.16
MgO	5 - 9	6.70
CaO	1 - 3	1.20
TiO <sub>2</sub>	0 - 1	0.80
Others	0 - 3	1.44

Manufactured by :



**TRANSWORLD  
GARNET**  
INDIA PVT. LTD.  
MAKING OUR ENVIRONMENT CLEANER

Palayamkottai High Road, Kuttudankadu Village,  
Tuticorin - 628 103, Tamil Nadu, India.  
Ph : +91 0461 2271519, 2271520  
Fax : +91 0461 2271541  
Email : sales@transworldgarnet.com  
Website : www.transworldgarnet.com



Year : 2016